



LEATHER CARE COMPANY

## TECHNICAL SCHEDULE LEATHER

### PANDA

Type of Leather:	bovine
Thickness:	mm. 0,9 – 1,00
Average size:	>= 45 pq
Tannage:	chrome salts
Dye:	aniline colouring
Aspect:	pigmented

### Technical Characteristic

<b>Analysis</b>	<b>Test Method</b>	<b>Units of measurement</b>	<b>Recommended Value</b>
Colour fastness to dry rubbing	UNI EN ISO 11640	Grey scale	>=4 a 500 cycles
Colour fastness to wet rubbing	UNI EN ISO 11640	Grey scale	>=4 a 250 cycles
Colour fastness to alkaline sweat	UNI EN ISO 11640	Grey scale	>=3/4 a 80 cycles
Finish adhesion	UNI EN ISO 11644	N/Cm	>=2
pH	UNI EN ISO 4045	-	>= 3,2
Tear strenght	UNI EN ISO 3377-1	N	>=20
Dry flexing	UNI EN ISO 5402	-	>= 20.000
Colour fastness to light xenotest	UNI EN ISO 105 B02	Blue scale	>=5

All submitted tests results are obtained using official methods on non-manipulated leather. Eventual further tests made after using leather, must be agreed between producer and buyer.