



LEATHER CARE COMPANY

TECHNICAL SCHEDULE LEATHER

BONANZA

Type of Leather:	bovine
Thickness:	mm. 1,00
Average size:	>= 45 pq
Tannage:	chrome salts
Dye:	aniline drum
Finishing:	mixed oil, wax and ecological polyurethane
Aspect:	natural grain with clearing up effect (pull up)

Technical Characteristic

Analysis	Test Method	Units of measurement	Recommended Value
Colour fastness to dry rubbing	UNI EN ISO 11640	Grey scale	>=3 a 50 cycles
Colour fastness to wet rubbing	UNI EN ISO 11640	Grey scale	>=3 a 20 cycles
pH	UNI EN ISO 4045	-	>= 3,2
Tear strenght	UNI EN ISO 3377-1	N	>=20
Colour fastness to light xenotest	UNI EN ISO 105 B02	Blue scale	>=3

All submitted tests results are obtained using official methods on non-manipulated leather. Eventual further tests made after using leather, must be agreed between producer and buyer.